


Refractory Sheet Types RS-100 and RS-200 boards are fiber reinforced structural alumina composites with useful properties in **thermal, structural and electrical insulation applications to 1260°C(2300°F)**. **Refractory Sheet Type RS- 100** has compressive and flexural strengths in the range of high temperature reinforced plastics, such as G-10 laminates, but retains its strength and utility to levels far exceeding the maximum use temperatures of plastics. Mechanical properties of Type RS-100 sheet far exceed those of asbestos-cement materials and is an excellent replacement for these rigid asbestos-containing products. Therefore, Type RS-100 not only makes an excellent replacement for rigid asbestos-containing products, but it can also be employed at much higher temperatures.

Type RS-100 is 100% inorganic, non-flammable and contains no asbestos or Refractory Ceramic Fiber (RCF). Its high alumina content makes it highly resistant to many environments, including molten aluminum, and it undergoes no out-gassing upon heating. It is not brittle and has high impact resistance. Type RS- 100 may be cut and machined with standard tooling.

Refractory Sheet Type RS-200 boards have all the properties of Type RS- 100 but exhibit higher strength due to a finer reinforcement structure. This makes Type RS-200 ideal for applications where intricate machining detail is needed. It is not brittle and has high impact resistance. Type RS-200 may be cut and machined with standard tooling.

Refractory Sheet Type RS-1200 boards are made from a combination of strong reinforcing fibers tightly bound in an alumina ceramic matrix. Type RS-1200 exhibits slightly lower compressive and flexural strength than RS-100. Type RS-1200 is completely inorganic and contains no asbestos or RCF fibers. It also exhibits greater refractoriness and homogeneity than other reinforced alumina matrix composite products and can be readily machined with conventional carbide tooling.



SUGGESTED APPLICATIONS

- Induction Furnace Components such as Coil Support Posts, Coil Liners, Furnace Tops, Crucible Bases, Front and Back Plates
- Electrical Terminal Blocks and Supports for Electrical Resistor Grids Operating in High Temperature Environments
- Exterior Structural Insulation in High Temperature Electrically Heated and Gas Fired Furnaces
- Hot Face Structural Insulation in Glass Tempering and Annealing Furnaces
- Brazing Separators and Fixtures
- General Protective Heat Shielding in Foundry Environments
- Insulation in High Pressure Molding Presses
- Hearth plates and Furnace Shelving

ZIRCAR Refractory Composites, Inc.

P.O. BOX 489, FLORIDA, NY 10921-0489
Tele: (845) 651-2200, Fax: (845) 651-1515
e-mail: sales@zrci.com
Home page: <http://www.zrci.com>

Technical Data
Bulletin No. ZRCI-001
Rev. September 2019

ALUMINA COMPOSITES MATERIALS

ZIRCAR Refractory Sheet Type RS-101, RS-201 and RS-202 are fiber reinforced ceramic laminate cylinders with useful properties to 1260°C(2300°F). These high temperature products offer high strength, moderate thermal conductivity and excellent electrical insulation. They retain their strength and utility to levels far exceeding maximum use temperatures of reinforced plastics and asbestos cement replacements. They are 100% inorganic, non-flammable and contain no asbestos. Their high alumina content makes them resistant to many environments including molten aluminum. They undergo little or no outgassing on heating, are not brittle, and may be cut and machined with standard tooling. Type RS-101 can be made into large cylinders with thick strong walls.

Compared to ZIRCAR Refractory Sheet Type RS-101 Cylinders, Type RS-201 has the following attributes:


- Finer reinforcement structure which allows for machining of intricate detail
- Less tendency to delaminate when machined
- Higher strength

Type RS-201 has a highly burnished outside surface which is ideal when the OD is crucial for liner placement. Type RS-202 has an as formed surface. They are available in both standard and custom size cylinders and are useful as induction coil liners, induction furnace components, and molten metal transport tubes.

ZIRCAR Refractory Sheet Cylinders are ideal when used in place of mullite tubing in high thermal shock applications.




Type RS-101 Cylinders are available in many sizes.



Type RS-201 (left) has a smooth burnished outside surface, Type RS-202's exterior texture reflects the weave of its reinforcing material.

SUGGESTED APPLICATIONS

- Induction Coil Liners in Induction Melting Furnaces.
- Molten Metal Splash Guards in Induction Furnaces.
- Direct Replacement for Asbestos Cement Products
- Fireproof Structural Insulation
- Electrical Insulation, Terminals and Supports
- Induction Furnace Components
- Electric Insulation for Aluminum Pot Ducting Systems



Type RS-101 Induction Coil Liner used in channel induction melting furnace

ZIRCAR Refractory Composites, Inc.

P.O. BOX 489, FLORIDA, NY 10921-0489
Tele: (845) 651-2200, Fax: (845) 651-1515
e-mail: sales@zrci.com
Home page: <http://www.zrci.com>

Technical Data
Bulletin No. ZRCI-001
Rev. September 2019

ALUMINA COMPOSITES MATERIALS

PHYSICAL PROPERTIES AND CHARACTERISTICS

TYPE	RS-100	RS-1200	RS-200	RS-101	RS-201 AND RS-202
Nominal Composition, wt%					
Al ₂ O ₃	75	82	65	65	65
SiO ₂	16	12	21	21	21
Other Metal Oxides	9	6	14	14	14
Organic content	0	0	0	0	0
Density, gm/cc(pcf)	2.1(130)	2.16(135)	2.1(130)	1.6(100)	2.1(130)
Porosity, %	35	31	30	35	30
Color	White to tan	White	White to tan	White to tan	White to tan
Max. Use Temp. *, °C(°F)	1260(2300)	1300(2370)	1260(2300)	1260(2300)	1260(2300)
Modulus of Rupture**, MPa(psi)					
as received	55(8000)	31(4500)	69(10,000)	16.6(2400)	69(10,000)
after 24 hrs at 600°C(1112°F)	36(5200)		31(4500)		
after 24 hrs at 1010°C(1850°F)					21(3000)
Compressive Strength**, MPa (psi)					
at 10% compression	69(10,000)	55(8000)	90(13,000)	69(10,000)	90(13,000)
Specific Heat, J/kg°K(BTU/lb°F)					
at 600°C(1100°F)	1172(0.28)	1172(0.28)	1172(0.28)	1172(0.28)	1172(0.28)
Flammability	Nil	Nil	Nil	Nil	Nil
Thermal Conductivity [‡] , W/m°K(BTU/hr. ft ² °F/in)					
204°C(400°F)	0.62(4.3)	0.62(4.3)	0.62(4.3)	0.62(4.3)	0.62(4.3)
427°C(800°F)	0.65(4.5)	0.65(4.5)	0.65(4.5)	0.65(4.5)	0.65(4.5)
649°C(1200°F)	0.66(4.6)	0.66(4.6)	0.66(4.6)	0.66(4.6)	0.66(4.6)
1010°C(1850°F)	0.68(4.7)	0.68(4.7)	0.68(4.7)	0.68(4.7)	0.68(4.7)
Thermal Expansion, RT-400°C(752°F)	6.0 x10 ⁻⁶ /°C (3.3 x10 ⁻⁶ /°F)	9.0 x10 ⁻⁶ /°C (5.0 x10 ⁻⁶ /°F)	8.0 x10 ⁻⁶ /°C (4.4 x10 ⁻⁶ /°F)	8.0 x10 ⁻⁶ /°C (4.4 x10 ⁻⁶ /°F)	8.0 x10 ⁻⁶ /°C (4.4 x10 ⁻⁶ /°F)
Linear Shrinkage, %					
after 4 hrs. at 1200°C(2200°F)	1 - 2	0.7 - 1	0.7 - 1	2	<1
Moisture Content, % at 105°C(220°F)	0 - 2	0 - 2	0 - 2	0 - 2	0 - 2
Loss on Ignition, % at 982°C(1800°F)	1 - 2	1 - 2	1	1	<1
Hardness, Durometer "D"	90	85	98	90	98
Electrical Properties					
Volume Resistivity, ohm-cm	7.2 x10 ¹¹		1.7 x 10 ¹²	9.6 x 10 ⁹	1.0 x 10 ¹⁰
Dielectric Strength, Volts/mil	71		26	26	26
Breakdown Voltage, KV (1/8" thick piece)	7.3				
(1/2" wall thickness)				14.1	
Arc resistance, sec.	>420	>420	>420	>420	>420

* Maximum use temperature is dependent on variables such as stresses, both thermal and mechanical, and the chemical environment that the material experiences.

** Properties expressed parallel to thickness.

‡ Properties expressed perpendicular to thickness.

ZIRCAR Refractory Composites, Inc.

P.O. BOX 489, FLORIDA, NY 10921-0489
 Tele: (845) 651-2200, Fax: (845) 651-1515
 e-mail: sales@zrci.com
 Home page: <http://www.zrci.com>

Technical Data
 Bulletin No. ZRCI-001
 Rev. September 2019

ALUMINA COMPOSITES MATERIALS

AVAILABILITY

Item #	Description	Item #	Description
AS01	RS-1200, 24" X 24" X 1/8"	BS01	RS-100, 24" X 24" X 1/8"
AS02	RS-1200, 24" X 24" X 3/16"	BS02	RS-100, 24" X 24" X 3/16"
AS03	RS-1200, 24" X 24" X 1/4"	BS03	RS-100, 24" X 24" X 1/4"
AS04	RS-1200, 24" X 24" X 3/8"	BS04	RS-100, 24" X 24" X 3/8"
AS05	RS-1200, 24" X 24" X 1/2"	BS05	RS-100, 24" X 24" X 1/2"
AS06	RS-1200, 24" X 24" X 3/4"	BS06	RS-100, 24" X 24" X 3/4"
AS07	RS-1200, 24" X 24" X 1"	BS07	RS-100, 24" X 24" X 1"
AS08	RS-1200, 24" X 24" X 2"	BS20	RS-100, 24" X 48" X 1/8"
AS20	RS-1200, 24" X 48" X 1/8"	BS21	RS-100, 24" X 48" X 3/16"
AS21	RS-1200, 24" X 48" X 3/16"	BS22	RS-100, 24" X 48" X 1/4"
AS22	RS-1200, 24" X 48" X 1/4"	BS23	RS-100, 24" X 48" X 3/8"
AS23	RS-1200, 24" X 48" X 3/8"	BS24	RS-100, 24" X 48" X 1/2"
AS24	RS-1200, 24" X 48" X 1/2"	BS25	RS-100, 24" X 48" X 3/4"
AS25	RS-1200, 24" X 48" X 3/4"	BS26	RS-100, 24" X 48" X 1"
AS26	RS-1200, 24" X 48" X 1"	BS30	RS-100, 24" X 48" X 2"
AS27	RS-1200, 24" X 48" X 2"	BS50	RS-100, 36" X 36" X 1/4"
AS50	RS-1200, 36" X 36" X 1/4"	BS51	RS-100, 36" X 36" X 3/8"
AS51	RS-1200, 36" X 36" X 3/8"	BS52	RS-100, 36" X 36" X 1/2"
AS52	RS-1200, 36" X 36" X 1/2"	BS53	RS-100, 36" X 36" X 3/4"
AS53	RS-1200, 36" X 36" X 3/4"	BS54	RS-100, 36" X 36" X 1"
AS54	RS-1200, 36" X 36" X 1"	BS59	RS-100, 48" X 48" X 1/8"
AS55	RS-1200, 36" X 36" X 2"	BS60	RS-100, 48" X 48" X 1/4"
CS01	RS-200, 18" X 24" X 1/16"	BS61	RS-100, 48" X 48" X 3/8"
CS02	RS-200, 18" X 24" X 1/8"	BS62	RS-100, 48" X 48" X 1/2"
CS03	RS-200, 18" X 24" X 1/4"	BS63	RS-100, 48" X 48" X 3/4"
CS04	RS-200, 18" X 24" X 1/2"	BS64	RS-100, 48" X 48" X 1"
CS20	RS-200, 24" X 36" X 1/16"	BS65	RS-100, 48" X 48" X 2"
CS21	RS-200, 24" X 36" X 1/8"	FS01	RS-101, 2" ID X 2 1/2" OD X 36"
CS22	RS-200, 24" X 36" X 1/4"	FS02	RS-101, 3" ID X 3 1/2" OD X 36"
CS23	RS-200, 24" X 36" X 1/2"	FS03	RS-101, 4" ID X 5" OD X 36"
		FS04	RS-101, 5" ID X 6" OD X 36"
		FS05	RS-101, 6" ID X 7" OD X 36"
		FS06	RS-101, 7" ID X 8" OD X 36"
		GS01	RS-201, 1" ID X 1 1/4" OD X 36"
		GS02	RS-201, 1" ID X 1 1/2" OD X 36"
		GS03	RS-201, 2" ID X 2 1/4" OD X 36"
		GS04	RS-201, 2" ID X 2 1/2" OD X 36"
		GS05	RS-202, 1" ID X 1 1/4" OD X 36"
		GS06	RS-202, 1" ID X 1 1/2" OD X 36"
		GS50	RS-202, 2" ID X 2 1/4" OD X 36"
		GS51	RS-202, 2" ID X 2 1/2" OD X 36"

Custom boards, shapes and preparations are available on request. Our forming processes, large inventory of custom tooling and state of the art machining techniques allow a wide variety of sizes and shapes to be made. Special geometries such as disks, rings and custom-machined shapes can be fabricated. Tight tolerance machining, compositional variations and the application of surface rigidizers and hardening agents are available. Please contact us with your special requirements.

Our forming process allows a wide range of cylinders to be made. Type RS-101 cylinders can be made from inside diameter of 3/4" with lengths to 72", to inside diameter of 36" with lengths to 36". Types RS-201 and RS-202 cylinders can be made from inside diameter of 1/2" with lengths to 72", to inside diameter of 36" with lengths to 36".

ZIRCAR Refractory Composites, Inc.

P.O. BOX 489, FLORIDA, NY 10921-0489
Tele: (845) 651-2200, Fax: (845) 651-1515
e-mail: sales@zrci.com
Home page: <http://www.zrci.com>

Technical Data

Bulletin No. ZRCI-001
Rev. September 2019